




RECOMMENDED FABRICS
50/50 Cotton/Polyester Blends
100 Polyester




INK APPLICATION
Guardian Black™ 1240 must be printed without any modifications in order to maintain the best bleed resistance of the product



ADDITIVES
Not recommended



SCREEN MESH
83-160 t/in (32-63 t/cm)
monofilament



EMULSION
Any direct or indirect solvent resistant emulsion or capillary film in the 35 to 70 micron range



SQUEEGEE
65-75 Durometer
Sharp edge.



CURE TEMPERATURES
275°F-325°F (135°C-163°C)
entire ink file and dependent on topcoat used



CLEAN-UP
Any eco-friendly plastisol type screen wash



PRODUCT PACKAGING
Quart, 1 gallon, 5 gallon, 30 gallon, or 50 gallon containers



STORAGE OF INK CONTAINERS
65° to 90°F (18°C to 32°C). Avoid storage in direct sunlight. Keep containers well sealed



SDS
Refer to SDS prior to use

FEATURES

AXEON™ Guardian Black™ 1240 blocks dye migration on problem fabrics that contain polyester, including sublimated dyed fabrics.

Guardian Black™ 1240 can take a variety of top coats depending on application; from low cure products to regular temperature curing products.

Guardian Black™ 1240 offers superior bleed resistant properties, but on some problem fabrics it may be possible for bleeding or dye migration to occur.

SPOT FLASHING

Guardian Black™ 1240 will spot dry, with a very low after flash tack. Dwell time is dependent on the spot dryer used. In some cases, you may have to lower the heat of the spot cure unit because too much heat may actually make the ink tacky. When you spot dry, you are only partially fusing or gelling the surface of the ink. The ink should be just dry to the touch, with no lift-off, but not totally fused. Totally fusing the underprint may cause inter-coat adhesion problems with the inks printed on top. Final fusing or curing should occur in the dryer. Failure to fuse ink properly may cause cracking, poor adhesion and poor wash fastness.

NOTE: FOR BEST RESULTS

For best print and blocking results, print two passes of Guardian Black™ 1240 through a 110 mesh screen. Then in sequence, Print-Flash-Print-Top Coat using a low bleed white ink or other type of low bleed performance ink.

IMPORTANT INFORMATION

Always test print the fabric to be used before beginning production to see if the desired performance is obtained.

It is very important that Guardian Black™ 1240 be exactly registered with any white or other color that is printed on top of the Guardian Black™ 1240 in order to help insure maximum bleed resistance of the top color. If the color printed on top of Guardian Black™ 1240 overlaps the Guardian Black™ 1240 in any spot, that spot may show bleeding or dye migration.

Test dryer temperatures and wash test printed product before and during a production run.

This ink and those in the **AXEON™** product line are not formulated with PVC resins or phthalate plasticizers, nor are they intentionally added.

Care should be taken to not cross-contaminate the **AXEON™** products with PVC or phthalate containing products.

Do not use standard plastisol curable reducers with this or any of the **AXEON™** products.

LEGAL DISCLAIMER

Recommendations and statements made are based on International Coatings' research and experience. Since International Coatings does not have any control over the conditions of use or storage of the product sold, International Coatings cannot guarantee the results obtained through use of its products. All products are sold and samples given without any representation of warranty, expressed or implied, of fitness for any particular purpose or otherwise, and upon condition that the buyer shall determine the suitability of the product for its own purpose. This applies also where rights of third parties are involved. It does not release the user from the obligation to test the suitability of the product for the intended purpose and application.

REV. 2400002